


RUSTIC BLACK

PORCELAIN



DESCRIPTION: Manufactured with high standards, our Porcelain range comes with a classic collection of various colours. It combines natural high slip resistance with strength, making it suitable for both pedestrian and trafficked areas. The manufacturing facility is accredited with ISO 9001:2015 and SA 8000:2014 certifications.

APPLICATIONS


| INTERIOR FLOOR | INTERIOR WALL | SHOWER WALL | SHOWER FLOOR | EXTERIOS FLOOR | EXTERIOR WALL | POOL/ FOUNTAIN | COUNTERTOP |
|----------------|---------------|-------------|--------------|----------------|---------------|----------------|------------|
| √ | √ | √ | √ | √ | √ | √ | |



SUMMARY OF KEY TECHNICAL DATA

| STANDARD | TEST | | RESULT |
|---------------|--|---------------------------------|---|
| EN : 10545-3 | Water Absorption | Average (% by mass) | 0.09 |
| | | Individual (% by mass) | 0.15 |
| EN : 10545-4 | Breaking Strength | | 4600 |
| EN : 10545-4 | Flexural Tensile Strength or Modulus of Rupture | Average (N/mm ²) | 40.5 |
| | | Individual (N/mm ²) | 36.5 |
| EN : 10545-6 | Abrasion Resistance | | Deep Abrasion (mm ³) |
| EN : 10545 | Anti slip Resistance Test (R11) | Wet | 26.8 (shall be non-slip tiles) |
| | | Dry | 26.9 (shall be non-slip tiles) |
| EN : 10545-9 | Thermal Shock Resistance, 10 cycles | | Withstand. No damage or cracks observed |
| EN : 10545-1 | Crazing Resistance Test | | Passes the test. No crazing observed |
| EN : 10545-1 | Frost Resistance | | Passes the test. Shall be no damage |
| EN : 10545-13 | Resistance to low concentration of acid and alkali | | Passes the test. No visual change. |
| | Resistance to high concentration to acid and alkali | | Passes the test. No visual change. |
| | Resistance to household chemical and swimming pool salts | | Class 'A' |

VARIATIONS



INSTALLATION & MAINTENANCE

| GROUTING | SEALER | LAYOUT | DRY LAYOUT | BASE |
|----------|-------------|--------|------------|----------------------------|
| 5 mm | RECOMMENDED | | | FULL MORTAR BED 4 TO 1 MIX |

PROJECT IMAGE

