

9kg
20lbs



Jointing Grout

Suitable for **Porcelain & Ceramic**



Internal & External Use



Rapid Setting



Water Repellent



Stain Resistant

Jointing Grout available in:



Black



Grey



Buff



Brown

Added Features & Benefits

- ✔ Joint width 1-15 mm
- ✔ Joint depth of 1-20mm
- ✔ Rapid setting
- ✔ Easy to apply
- ✔ Water repellent
- ✔ Internal & External use
- ✔ Efflorescence free
- ✔ Stain resistant
- ✔ Hygienic anti-mould

Pavetuf Jointing Grout

Designed as a flexible wall and floor grout for both external and internal applications, that can be used with under-floor heating. The fine texture provides a smooth, satin, mould and water resistant finish that is suitable for use on porcelain and ceramic tiles and paving. This bucket contains 3 x 3kg bags.

Preparation

Allow adhesive / mortar bed to set sufficiently before applying grout. Ensure the joints are clean, and free from dust or any other contamination. Any obstructions more than 1/3 the joint depth, should be removed.

In very warm conditions or with very porous tiles / paving it is recommended to dampen the joints before grouting. Pavetuf Jointing Grout is suitable for use in joints of 1-15mm on a depth of 1-20mm.

Recommendations:

- Use one bag at a time and mix in the bucket provided.
- Substrates must be stable and free from excessive movement.
- It is advisable to carry out a trial on a test area when colour is critical.
- Slight batch to batch colour variation may occur. It is recommended to always use grout from the same batch or premix grout from different batches before use.
- Setting and drying times are affected by site temperatures and conditions - Do not use under 5°C.
- Grout residue remaining on the surface of the tile after hardening may need to be removed with Pavetuf's Deep Cleaner. This should be carried out with care after 24 hours and the joints pre-wetted.
- Swimming pools should not be filled for 3 weeks after grouting.
- Always read the current technical and safety data sheet before use, these can be accessed on www.pavetuf.co.uk

Shelf Life

12 months when stored in unopened bags in dry conditions.

For further information on using Pavetuf Jointing Grout and for recommendations on construction please contact us:



Call 0330 333 8030
Visit www.pavetuf.co.uk



Call (888) 240 8704
Visit www.naturalpavingusa.com

Mixing and Grouting

- 1) Mix powder with clean water (approx. 750ml per 3kg bag) to a thick creamy paste using a slow speed drill and paddle (you can use the bucket provided)
- 2) Allow the mixed grout to stand for 2-3 minutes then remix briefly to ensure an even consistency. The mixed grout is usable for 30-40min depending on temperature. Do not add water or attempt to remix after the grout has begun to set.
- 3) Work the grout into the joints using a grouting trowel, small squeegee or sponge to ensure a well filled and compacted joint.
- 4) Remove the excess grout from the tile surface as grouting proceeds.
- 5) After initial stiffening of the grout (typically around 30min) clean the tile surface using a clean dampened sponge working diagonally across the grout lines.
- 6) When the grout is suitably set, polish the surface with a clean dry cloth.
- 7) Tiled and paved areas will be ready for light foot traffic after approx. 3 hours and full traffic after 24 hours.

Coverage

Coverage is dependent on the size of the tile and joint. As an example, with a 600 x 600 x 20mm tile and 5mm joint, a 3kg bag of Pavetuf Jointing Grout will cover ~7.5m²

Safety & Precautions

No significant hazard.

Pavetuf Jointing Grout does not contain Portland cement, but may be slightly alkaline in contact with water, sweat etc.

- Avoid prolonged contact with skin.
- Wear gloves and avoid contact with eyes.
- Keep out of reach of children.
- Wash skin with soap and water after contact.

This grout contains a biocide to protect the dried surface from fungal growth.

Biocidal Content

Contains: 2-octyl-2H-isothiazol-3-one.

Distributed worldwide by Talasey Ltd
www.talasey.co.uk

